




Premium Coil Coatings - *Cool Roof*


STANDARD COLOR CHART

40 - YEAR WARRANTY

86 Breezy Point Pl.
 The Woodlands, TX 77381
 Jerry Jones: 713-492-9123
 Aaron Funderburke: 832-465-7339



POLAR WHITE*



LIGHTSTONE*



DESERT SAND



SADDLE TAN*



RUSTIC RED



COCOA BROWN



BURNISH SLATE



CHARCOAL



ASH GRAY*



HAWAIIAN BLUE



EVERGREEN




IVY GREEN*



BURGUNDY



COPPER PENNY



GALVALUME

Check availability on the following colors



IVORY



BLACK



CRIMSON RED



SILVER METALLIC

* Also available in a 10-year commodity.
 Inquire as to the availability of other colors.



These color samples are as close as possible to actual colors offered, within the limitations of color chip reproduction.



XT-40S Ceramel™

Premium Exterior Coil Coating System

Dura Coat Products XT-40S Ceramel™ exterior Silicone Modified Polyester (SMP) is a custom hybrid topcoat. When combined with DC477 Global Primer, this coating system offers the highest expectations for long term field performance while retaining the best results for color and gloss retention.

XT-40S Ceramel™ is available in ceramic and “Cool Roof” pigments and is Energy Star and Cool Roof Rating Council (CRRC) compliant. A wide variety of colors are available as well as gloss, low sheen applications. The XT-40S Ceramel™ system provides the best hardness to flexibility ratio when compared to other competitive systems in the marketplace. The system provides for the ultimate protection against scratching, marring and transit abrasion.

XT-40S Ceramel™ is also available with additives Microban® and DuPont Teflon® and supports the toughest and most competitive warranty position in the market.

Performance Characteristics

SPECIFICATION	TEST	RESULTS
ASTM D-523	60° Specular Gloss	10-80 Gardner 60° meter or equivalent
ASTM D-3363	Pencil Hardness	H-3H No break in the film
ASTM D-4145	Coating Flexibility	1T-2T No pick off with Scotch #610 tape Substrate specific
ASTM D-2794	Reverse Impact, 60-80 inch pounds	Passes No pick off with Scotch #610 tape
ASTM G-53	Q.U.V. Weatherometer, 1000 hours	Passes No objectionable chalking per ASTM D-659, color change per ASTM D-2244 or blistering per ASTM D-714
ASTM D-2247	Humidity, 1000 hours at 100°F and 100% Humidity	Passes Less than 5% No. 8 blisters
ASTM B-117	Salt Spray 1000 hours 5% Salt Solution	Passes Less than 5% No. 6 blisters and Less than 1/8" creep or tape off from the scribe per ASTM D-1654
ASTM D-2244-89	45° So. Florida Exposure 20 years, color retention	Passes No objectionable, color change, Less than 5 units color change
ASTM D-659-86	45° So. Florida Exposure 20 years, chalk resistance	Passes No objectionable, gloss loss or chalking Rating of 6 min.