

SPECIFIER'S NOTE:

SPLASHMAX USES THE SAME TOP LAYER AS THAT USED ON OUR POLYMAX PLAYGROUND SURFACING.

THE FOLLOWING ASTM E303 TESTING WAS DONE USING A POLYMAX TOP CAP LAYER. THIS TOP LAYER IS IDENTICAL TO THAT USED IN SPLASHMAX.

BECAUSE OF THIS, WE ARE USING THE POLYMAX TESTING AS EQUALLY APPLICABLE TO SPLASHMAX TO AVOID DUPLICATION OF EFFORTS.



TEST REPORT

CLIENT:

Company:	PlayMax Surfacing Inc.	Report Number:	66156A
Address:	1950 Compton Avenue, Suite 111	Lab Test Number:	2777-6204
	Corona, CA 92881	Test Completion Date:	1/29/2016
		Report Date:	2/1/2016
		Page:	1 of 1
Requested By:	Chris Wolf		

TEST MATERIAL:

Material Type:	PIP Playground Surfacing Top Cap				Date Received:	12/28/2015
Material Condition:	EXCELLENT:	XXX	GOOD:		POOR:	REJECTED:
Style:	PolyMax®					
Description:	½" Thick polyolefin beads and crystal clear aliphatic binder					

TESTING METHODS REQUESTED:

<i>Testing Services Inc. was instructed by the client to test for the following...</i>	
Standard:	ASTM E303-93(2013) Test Method: Standard Test Method for Measuring Surface Frictional Properties Using the British Pendulum Tester

SAMPLING PLAN:

Sampling Date:	12/28/2015
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION	TEST RESULT	
ASTM E303-93(2013)	Skid Resistance	Average of both Directions	51.6 BPN

- Under NVLAP guidelines, TSI is to report any outsourcing of testing to another laboratory facility.
- In the above testing, all of tests were outsourced to : Future Labs, LLC. Their accreditations are on file and available upon request.

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

 Erle Miles, Jr. VP, Testing Services Inc

TSI Accreditation: Our laboratory is accredited by the US Dept of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0.

Form:	Rev:	Revision Date:	Page 1 of 1
Release Date:	Control Type: Electronic – Expires 24 hours after this date: Feb. 3, 16 Printed copies are uncontrolled		

817 Showalter Avenue * PO Box 2041
Dalton, GA 30722-2041
(706) 226-1400
tsioffice@optilink.us

OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, INC. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. THE REPORTS AND LETTERS, AND OUR NAME, OUR SEALS, OR OUR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.