



ERAOS-DTA-958BTC535P110
REV2.0
DATE: 25/09/23

# ERA TorQ

## 9 5/8 BTC 53.5ppf P110

### Pipe

Plain End Weight	Wall Thickness	Inside Diameter	Drift Diameter	Pipe grade	Body Yield Strength	Internal Yield Plain End	Collapse Pressure
Lbs/Ft	Inches	Inches	Inches		Lbs	PSI	PSI
53.50	0.545	8.535	8.379	P110	1,710,000	10,900	7,930

### Connection Dimensions with ring

Coupling Outside Diameter	Connection Yield Strength	REGULAR Coupling Length	REGULAR Make-up Loss	ERA TorQ ring height	ERA TorQ ring OD	ERA TorQ ring ID
Inches	Lbs	Inches	Inches	Inches	Inches	Inches
10.625	1718000	10.625	4.813	0.921	9.320	8.535

### Torque

FT LBS APPLIED	Min Make up	MAX NO TORQUE TURN	MAX WITH TORQUE TURN
PIN / RING CONTACT	9,630	9,630	9,630
DELTA TORQUE	20181	40,362	50,453
Total	29,811	49,992	60,083

Note 1: For maximum field efficiency ensure that TT computer monitoring is used if maximum torque figure is required. Note 2: Delta torque yield point of torque ring is 100,906 ftlbs. This means that the torque ring will collapse if you apply 100,906 ftlbs of Delta torque into the torque ring itself, excluding your pin / ring contact torque with triangle down.

For further information on field application parameters please contact:  
 ERA Oilfield Service (Thailand) Co Ltd., 66/69 Moo 4, Soi 17, Phayun, Ban Chang, Rayong, Thailand 21130.  
 Tel: +66 8 4345 8730 Email: jim.reid@eraoilfieldservices.com