

TEST REPORT

CLIENT:

Company:	PlayMax Surfacing Inc.	Report Number:	65192C
Address:	1950 Compton Avenue, Suite 111 Corona, CA 92881	Lab Test Number:	2737-4645
		Test Completion Date:	October 1, 2015
		Report Date:	October 15, 2015
		Page:	1 of 1
Requested By:	Chris Wolf		

TEST MATERIAL:

Material Type:	PIP Playground Surfacing Top Cap	Date Received:	8/6/2015
Material Condition:	EXCELLENT: XXX GOOD: POOR: REJECTED:		
Style:	MaxPour® Supreme		
Description:	½" Thick TPV (fine-granule) Rubber Granule Top Cap		

TESTING METHODS REQUESTED:

<i>Testing Services Inc. was instructed by the client to test for the following...</i>			
Standard:	ASTM E303-93(2013)	Test Method:	Standard Test Method for Measuring Surface Frictional Properties Using the British Pendulum Tester

SAMPLING PLAN:

Sampling Date:	8/6/2015
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION	TEST RESULT	
ASTM E303-93(2013)	Skid Resistance	Average of both Directions	53.9 BPN

➤ Under NVLAP guidelines, TSI is to report any outsourcing of testing to another laboratory facility. In the above testing, all of tests were outsourced to : Future Labs, LLC. Their accreditations are on file and available upon request.

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

Erle Miles, Jr. VP, Testing Services Inc

TSi Accreditation: Our laboratory is accredited by the US Dept of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0.

Form:	Rev:	Revision Date:	Page 1 of 1
Release Date:	Control Type: Electronic – Expires 24 hours after this date: Oct. 15, 15 Printed copies are uncontrolled		