



TESTING SERVICES, INC.
 817 SHOWALTER AVE. • P.O. BOX 2041
 DALTON, GEORGIA 30722-2041
 PHONE: (706) 226-1400 • FAX: (706) 226-6118

TEST REPORT

CLIENT:

Company:	PlayMax Surfacing Inc.	Report Number:	65192F
Address:	1950 Compton Avenue, Suite 111	Lab Test Number:	2737-4645
	Corona, CA 92881	Test Completion Date:	October 13, 2015
		Report Date:	October 15, 2015
		Page:	1 of 1
Requested By:	Chris Wolf		

TEST MATERIAL:

Material Type:	PIP Playground Surfacing Top Cap			Date Received:	8/6/2015
Material Condition:	EXCELLENT:	XXX	GOOD:	POOR:	REJECTED:
Style:	MaxPour® Supreme				
Description:	½" Thick TPV (fine-granule) Rubber Granule Top Cap				

TESTING METHODS REQUESTED:

<i>Testing Services Inc. was instructed by the client to test for the following...</i>			
Standard:	ASTM D624-00(2012)	Test Method:	Standard Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers

SAMPLING PLAN:

Sampling Date:	8/6/2015
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION	TEST RESULT
ASTM D624-00 (2012)	Average Tear Strength	59.34 lbs/force/inch

Specimen 1	56.62 lbs//inch	Specimen 2	60.48 lbs//inch	Specimen 3	58.66 lbs//inch
Specimen 4	59.13 lbs//inch	Specimen 5	61.79 lbs//inch		

Conditioning/Test Environment: 70°F 65% RH Head Speed: 20"/minute

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

Erle Miles, Jr. VP, Testing Services Inc

TSI Accreditation: Our laboratory is accredited by the US Dept of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0.

Form:	Rev:	Revision Date:	Page 1 of 1
Release Date:	Control Type: Electronic – Expires 24 hours after this date: Oct. 15, 15 Printed copies are uncontrolled		