



MACRO-FLEX™

True rubberizing A/B Latex based additive that significantly improves the performance of sealcoatings.

Toughens Sealer Film

Enhances tensile strength, flexibility and adhesion properties of the cured sealer.

Boosts Viscosity

Enables sealer to suspend larger quantities of sand effectively.


Meets FAA Specification

Can allow a Refined Tar mix design the ability to meet FAA Specifications.



America's Most Trusted Sealcoating Additives and Pavement Protection Products

Get The Star-Seal Contractors Resource Smartphone App Today!



14041 Chrisman Rd. ▲ Houston, TX 77039

281-442-0050

www.lonestarsealcoat.com

MACRO-FLEX™

REINFORCES AND ADDS SUBSTANTIAL BENEFITS TO SEALCOATINGS

GENERAL DESCRIPTION

STAR MACRO-FLEX® is a true rubberizing, A/B (Acrylonitrile/Butadiene) latex based additive that significantly improves the performance of Refined Tar (RTS) and Asphalt Emulsion (AE) based sealcoatings. STAR MACRO-FLEX® reinforces sealcoatings in the most desirable aspects of toughness, flexibility, viscosity for sand suspension and overall resistance to petrochemicals and de-icing salts.

OUTSTANDING PROPERTIES

- Toughens the sealer film and improves tensile strength thus reducing power steering marks, scuffing and tearing. Improves flexibility and adhesion of the cured sealer film to the existing surface. Improves fuel and chemical resistance of the cured film.
- Improves flexibility and the ability to bridge minor surface (non-working) cracks in the pavement to eliminate water penetration and extend the life of asphalt surfaces.
- Boosts the viscosity of the diluted sealer and enables it to suspend large quantities of sand effectively and uniformly. Eliminates sand roll out, and the streaky appearance of a cured coating. Finished jobs will have a more uniform-textured appearance.
- Speeds up the drying time of sealcoatings.
- The addition of STAR MACRO-FLEX® can allow a Refined Tar mix design the ability to meet FAA Specifications.
- Based on a polymer-emulsion; safe to handle and use. No health hazards have been reported.

RECOMMENDED USES

STAR MACRO-FLEX® is recommended for applications where moderate to high traffic exists or environments with frequent abuse from harsh chemicals, de-icing salts, kerosene, gasoline, oils, petrochemicals, fat and grease. Used in applications at; Airport Runways and Taxiways, Fast Food Restaurants, Apartment Buildings, Truck Service Plazas, Gas Stations, Commercial and Industrial Complexes, Residential Driveways and many more.

LEVEL OF ADDITION

2-5% STAR MACRO-FLEX® by volume of the concentrated sealer
IT IS NECESSARY to pre-dilute STAR MACRO-FLEX®

MIX DESIGN (SUGGESTED)

	US	METRIC
Sealcoating	100 Gallons	100 Liters
Clean Potable Water	50 Gal. Max	50 Liters Max
Sand 50-70 AFS	300-500 Lbs.	36-60 Kg.
STAR MACRO-FLEX®/Water (1:1)	2-5 Gal.	2-5 Liters

MIXING TIPS

- Add water to the sealer and start agitation.
- **IMPORTANT:** Pre-mix STAR MACRO-FLEX® with an equal volume of water.
Caution - Water must be added into to STAR MACRO-FLEX®, not vice-versa
- With agitation on, add the STAR MACRO-FLEX®/water mixture to the diluted sealer and continue mixing for 5 minutes.
- Add the sand slowly, at a steady rate of about 100-lb. bag/minute.
- Continue to mix to a smooth consistency. Adjust the speed of mixer to turn the sealer mix sufficiently inside the tank without beating air into the mix. You may have to raise the speed during sand addition and reduce towards the end of the mix cycle.

IMPORTANT WEATHER LIMITATIONS

- Surface and air temperature should be a min. 50° F (10° C) and rising.
- Do not apply on rainy, foggy, or extremely humid days (max 80%), or when rain is in the forecast within 8 hours.
- Most favorable conditions are; humidity less than 60%, higher temperatures and lower relative humidity with mild wind velocity.

SPECIAL INSTRUCTIONS

- Do not add more than 5% of STAR MACRO-FLEX®. Beyond this limit, it will not add any performance benefit. Conversely, it may thin down the sealer mix.
- Do not add more sand than 5 lb./gallon of the concentrated sealer. Higher amounts of sand reduce the flexibility and adhesion of the cured sealer.
- Keep the water dilution rate below 50%. Excessive amounts of water will cut down the dry sealer film thickness, which in turn will result in pre-mature failure.
- Mix thoroughly before using and keep unused container properly sealed.
- **Using other additives or additives manufactured by companies other than STAR, Inc in conjunction with this product might produce undesirable results. Consult your STAR representative for recommendations.**

CAUTIONS

KEEP FROM FREEZING / KEEP OUT OF REACH OF CHILDREN
Wear gloves and protective clothing. In case of contact, flush skin or eyes immediately with fresh water. If the product gets in the mouth or eyes see a physician immediately. Consult a Safety Data Sheet for details.

PACKAGING & AVAILABILITY

5-Gallon plastic pails, 55-gallon drums and 275-gallon plastic totes at all STAR plant locations.

WARRANTY & DISCLAIMER Additives manufactured by S.T.A.R., Inc. are designed specifically for use with the RTS and AE Sealcoatings our Member Plants produce. The suggestions and related data contained on these pages are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. S.T.A.R., INC. will not be responsible for any indirect or consequential damages. We will either replace or refund the purchase price in the event the products are proved to be defective, at our option.



STAR
SPECIALTY TECHNOLOGY AND RESEARCH

WORLD-WIDE HEADQUARTERS
1150 Milepost Drive, Columbus, OH 43228
+1-800-759-1912 • www.starseal.com