



POLYIMIDE TAPE

Made with Polyamide Film with silicon resin.

Application:

As Class H insulation in motors and generators.

Sr. No.	Description	Units	Observed Values
1	Temperature index	-	upto 200°C
2	Thickness	mm	0.06 ±0.01
3	Elongation at Break	%	≥ 25
4	Break Down Volatge	Kv	≥ 6
5	Breaking Strength	N/cm width	≥ 40
6	Adhesion Strength	N/cm	2 min.

