

## **EPOXY MATT LAMINATE**

## EPGM203

Laminated Sheet made from layers of chopped strand glass matt, treated with Epoxy Resin having high temperature index unto 155°C.

The material has high mechanical and electrical properties. It has a good mating and punching properties.

It conforms to IEC 60893 specification.

Sr. No.	Description	Units	Observed Values
PHYSIC	AL		
1	Specific Gravity	g/cm <sup>3</sup>	1.8 ± 0.1
2	Water Absorption at 20°C for 24 hours	mg	22
3	Temprature Index	TI	155℃
MECHA	NICAL		
4	Flexural strength @ 23°C	Мра	≥ 320
5	Flexural strength @ 155°C	Мра	≥ 50%
6	Tensile strength	Мра	≥ 250
7	Compressive Strength ⊥	Мра	≥ 450
8	Compressive Strength II	Мра	≥ 250
9	Charpy Impact Strength (IZod)	Kj/m <sup>2</sup>	> 100
10	Volume Resistivity	Ohm.cm	0.125 x 10 <sup>12</sup>
11	Surface Resistivity	Ohm	2.16 x 10 <sup>12</sup>
ELECTR	ICAL		,
12	Electric strength in oil 90 °C - perpendicular	Kv/mm	≥ 15
13	Breakdown Voltage at 90°C in oil parallel to laminate	Kv	≥ 35
14	Insulation resistance after immersion in water	M-Ohms	≥ 5x10 <sup>7</sup>

