

Fabric Specification Sheet

4-Ply 17oz Wideshade IV

Style:	4-Ply 17oz Widesha	de IV	
Available Widths:	98", 120" (249 cm, 305cm) (Other widths and colors available, MOQ's may apply)		
Roll Lengths:	25 yard standard (Other lengths available upon request) (23 m)		
Shipping:	Rolls shipped on 3" (7.62 cm) ID paper core		
Construction:	4 ply laminate (70% Vinyl and 30% Fiberglass) (Each vinyl is equal thickness and weight)		
Surface Texture:	As Laminated – Various embossing patterns available		
Thread Count:	68 threads per square inch (26 per square cm)		
Weight:	17.9 oz per square yard (606 grams per square meter)	(+ or - 2.0) (+ or - 68)	
Thickness:	16.9 mil (.42 mm)	(+ or - 2.0) (+ or05)	
Instron Tear Strength:	Warp Fill 9 Lbs/In 10 Lbs/In		
Instron Breaking Strength:	Warp Fill 339 Lbs/In 256 Lbs/In		
Opacity: Visual check	Blackout		
Washability:	Material may be dusted with a damp cloth. When scrubbing is necessary, warm water, mild detergents and gentle rubbing are recommended.		
Flammability:	NFPA Standard 701/2015 Edition	n Test Method 1 (Small Scale)	
Other Tests Passed:	AATCC 183 – Blocking Ultraviole AATCC 16E-1993 – Colorfastnes ASHRAE Standard 74-1988 – Fe SW 846-7000B-7420 (Pb) – Lead UL GreenGuard Gold Certified	ss to Light enestration	
		SC (Single Glass)	SC (Insulating Glass)
		O-F 1/8" CI 1/4" CI 1/4" H.A 0.2 0.19 0.21 0.25	<u>1/2" CI</u> <u>1" CI</u> <u>1" H.A.</u> 0.19 0.22 0.2
ultra-fresh antimicrobial technology	NFPA® lead f		C.15 C.22 C.2

MAILING ADDRESS P.O. Box 1017 Warsaw, IN 46581 FAX (574) 269-7747

PHONE

(574) 269-1280

STREET ADDRESS 102 Enterprise Drive Warsaw, IN 46580

E-MAIL

Mail@Indianacoatedfabrics.com

WEBSITE www.indianacoatedfabrics.com