

NA-900EU cold bond rubber cement

A CFC free, two-component chloroprene based cold bonding cement designed to bond rubber, metal, fiberglass, fabric, concrete, and wood substrates together with excellent initial bond strength without the aid of heat, pressure, or special equipment.



The directions for the use of our products are based upon tests believed to be reliable but no warranty is given. Since conditions for the use of this product are beyond the sellers control, all risks are assumed by the user. Please contact your local agent or call Normac Adhesive Products Inc. for further assistance.

POT LIFE: The pot life of mixed 900EU cement is approximately 2 - 3 hours at 23°C (73°F)

COVERAGE: Approximately 6sqm (64sqft) per KG per one coat by brush

PRODUCT FEATURES:

Color: Clear, Black, FDA White Coats required: Two E Hardener ratio: 4.5% by weight Solids content: 17.5% Consistency: Brushable liquid Diluents: Ethyl Acetate, Naphtha, Toluene Flash Point: -20C Oil Resistance: Excellent Chemical Resistance: Good, PH level between 3 to 11 Metal Primer: NP-5001 Max Constant Operating Temp: 100C (212F) Rubber to Metal 80C (176F) Rubber to Rubber 80C (176F) Rubber to Fabric

APPLICATION CONDITIONS:

Ambient and substrate temperature: 7°C to 45°C (45°F to 113°F) Relative humidity: below 80% Dew point: 3°C (5°F) above dew point Protect from direct sunlight and surface contamination

TRANSPORTATION AND STORAGE

Transportation: DGR

Shelf life: 2+ years unopened when stored in a cool dark room under 23°C (73°F) and away from heat, sparks, and flame

PACKAGING AND KIT SIZE:

- Pint can / 0.33kg kit, includes 1 x 15g E-Hardener
- Quart can / 0.66kg kit, includes 1 x 30g E-Hardener
- Gallon can / 3.3kg kit, includes 5 x 30g E-Hardener
- 5 Gallon can / 16.5kg kit, includes 25 x 30g E-Hardener
- 55 Gallon drum / 190kg lit, includes 290 x 30g E-Hardener
- · Both cement and hardener can be purchased separately.

SAFETY

Flammable liquid. See the NORMAC NA-900EU product SDS. Strict adherence to regional safety regulations must be practiced.