



23010 Ryen Dr NW, Ste C. • Poulsbo, WA 98370-6406  
(360) 598-3090 • FAX (206) 494-7787

## PRODUCT SPECIFICATION SHEET

### 30mil LDPE

**General Description:** High density polyethylene woven fabric base complete with a low density coating.

		<b>TEST METHOD</b>
<b>Coating:</b>	LLDPE	
<b>Construction:</b>	Polyester Tapes	
<b>Thickness:</b>	30 mil	
<b>Weight:</b>	20 oz p.s.y.	
<b>Tensile Grab Strength:</b>	290 / 270	ASTM-D-5034
<b>Tongue Tear-Large Scale:</b>	warp 134 / weft 102	ASTM-D-751/NSF
<b>Trapezoid Tear:</b>	warp 260 / weft 115	ASTM-D-4533-04
<b>Burst:</b>	340 PSI	ASTM-D-3786-1
<b>Hydrostatic Resistance:</b>	321 PSI	ASTM-D-4833
<b>Typical Weld Values:</b>	Roll = 20 LB, Shear = 90 LB	
<b>Standard Width:</b>	12'	
<b>Low Temperature:</b>	-40 degrees	ASTM-D-2136-94
<b>Standard Colors:</b>	Black / Black	(Cabon Black 4.38%)
<b>Weatherability:</b>	Accelerated UVI treatment gives 95% strength retention after 2000 hours on weatherometer.	ASTM 653