



NATIONAL TESTING STANDARDS INC.
RESEARCH AND TESTING LABORATORIES

Report No. 29694-3

November 21, 2007

Client: Rust Bullet, LLC
300 Brinkby Ave., Suite 200
Reno, NV 89509-4359

Reference: David P. Ciglar

Subject: Salt Fog/Spray of Rust Bullet® Rust Coating.

Sample Description:

One coated metal panel was submitted by the Client and identified as Q panel coated with two brushed coats of Rust Bullet® paint.

This test panel had previously been exposed to 168 hours of weatherometer and thermal cycling.

Request:

Expose the submitted test panel to 500 hours (3 weeks) of salt fog/spray.

Method:

The panel was placed in a salt fog/spray chamber for 500 hours (3 weeks).

The chamber was operated in accordance with the procedures set forth in ASTM B-117 except actual sea water was used in place of the standard salt water.

Results:

The Rust Bullet® test panel exhibited corrosion along the scribe line with undercutting of less than 3/16".

NATIONAL TESTING STANDARDS

A handwritten signature in blue ink that reads "Lewis F. West".

by Lewis F. West