



G and G Partners LLC
306 Green Oaks Drive
League City, TX 77573
281-947-8069

N60 Blend Specifications

Type of Test	ASTM Method	Trans-X Typical Values
Color	D1500	1.0-2.0
Corrosive Sulfur	D1275	Non-corrosive
Water Content, ppm	D1533	<500ppm
Flash Point ° F	D92	280-300
Pour Point ° F	D97	- 40 Max
Specific Gravity 60/60	D1298	.880
Viscosity: Saybolt SUS		
100° F	D88	55-65
210°F	D2161	36
Viscosity: Kinematic cSt		
40°C	D445	10.4
100°C	D445	2.4