

ARAGONITE

TECHNICAL INFORMATION

Typical Analysis

(Dried unwashed sample)

| QUANTITATIVE | % BY WEIGHT | |
|--------------------------------|-------------|---------|
| | MINIMUM | MAXIMUM |
| CaCO ₃ | 94.00 | 98.50 |
| MgCO ₃ | 0.50 | 1.50 |
| SiO ₂ | 0.02 | 0.08 |
| Fe ₂ O ₃ | 0.008 | 0.025 |
| Al ₂ O ₃ | 0.02 | 0.15 |
| SO ₃ | 0.10 | 0.20 |
| NaCl | 0.06 | 0.25 |
| SrO | 0.30 | 1.25 |
| LOI | 43.50 | 45.00 |

Screen Size Specifications

(Natural / Commercial Grade)

| U.S. STANDARD MESH | PERCENT RETAINED |
|--------------------|------------------|
| 4 | 0 - 1 |
| 8 | 1 - 4 |
| 16 | 3 - 11 |
| 30 | 10 - 26 |
| 50 | 40 - 67 |
| 100 | 80 - 98 |
| 140 | 93 - 99 |
| 200 | 99 - 100 |

Moisture: 5% - 10%

This information is not to be taken as a warranty or representation for which we assume legal responsibility, nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation and verification.