

# BENTOBLOCK®

## LOW PERMEABILITY SEDIMENT CAP MATERIAL

### DESCRIPTION

BENTOBLOCK® is natural sodium bentonite screened to 3/8 inch (0.95 cm) to 3/4 inch (1.90 cm) in size. BENTOBLOCK® is certified to NSF/ANSI Standard 60, Drinking Water Treatment Chemicals - Health Effects.

### APPLICATIONS

**BENTOBLOCK® is specially formulated for use in the following applications:**

- Mix with aggregate and deploy as a low-permeability sediment cap
- Mix with aggregate and deploy as a low-permeability barrier as part of funnel and gate system.
- Deploy around submerged structures in conjunction with Bentomat CL geosynthetic clay liner.
- For freshwater applications only. For saline conditions, contact CETCO Technical Sales Manager.

### FEATURES

- Chemically stable. Results from TCLP Priority Pollutants analysis are below RCRA limits for hazardous constituents\*. NSF/ANSI Standard 60 certified.
- Creates self-sealing low-permeability layer.
- Provides a high-solids bentonite seal



Shown larger than actual size.

### MIXING AND APPLICATION

Bagged material should be screened of fines before placement. For waterway applications, deploy slowly directly over water surface and allow to settle through water column. Do not tremie through water.

### TESTING DATA

PHYSICAL PROPERTIES		
Property	Test Method	Results
Bulk Density	CETCO Test Method	67.30 lbs./ft <sup>3</sup> (1.08 kg/m <sup>3</sup> ), typical
Hydraulic Conductivity	ASTM D5084	2 x 10 <sup>-8</sup> cm/s*
Sieve, passing 100 mesh, AS SHIPPED	CETCO Test Method	≤ 1.5% maximum
Attrition, Ro-tap w/ steel bearings, 30 minutes	CETCO Test Method	<4% weight loss
Swell, 500 grams, @ 24 hours	CETCO Test Method	1100 ml, minimum

### PACKAGING

**BENTOBLOCK® is available in the following packaging option:**

- 2500 lb. (1,135 kg) super sack bag.

\* Historic data, available upon request.

North America: 847.851.1800 | 800.527.9948 | www.CETCO.com

© 2014 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.

UPDATED: NOVEMBER 2013

TDS\_BENTOBLOCK\_AM\_EN\_201311\_v1