



NATIONAL TESTING STANDARDS INC.
RESEARCH AND TESTING LABORATORIES

Report No. 29694-7

November 21, 2007

Client: Rust Bullet, LLC
300 Brinkby Ave., Suite 200
Reno, NV 89509-4359

Reference: David P. Ciglar

Subject: Chip Resistance of Rust Bullet® Coating.

Sample Description:

One coated metal panel was submitted by the Client and identified as Q panel coated with two brushed coats of Rust Bullet® paint.

Request:

Determine the chip resistance of the Rust Bullet® coating.

Method:

The panel was evaluated for chip resistance of the coating by the rapid deformation method in accordance with the procedures set forth in ASTM D-2794.

Results:

The Rust Bullet® test panel exhibited cracking of the film at the 28 inch pound level of impact.

NATIONAL TESTING STANDARDS

by Lewis F. West