

POLYESTER GLASS LAMINATE

NEMA GPO3

Laminated Sheet made from layers of fine glass mat, treated with Resin having high temperature index unto 150°C.

The material has high mechanical and electrical properties. It has a good mating and punching properties. It offers excellent flame, arc and track resistance.

Common Applications are in generators, transformers and railways components.

Testing Standard: NEMA GPO3

| S I. No. | Properties | Unit | Observed Values |
|----------|---|-------|----------------------|
| 01. | Physical Appearance | | Smooth |
| 02. | Flexural Strength at Room Temperature | MPa | >250 |
| 03. | Flexural Strength at 150°C | Мра | >125 |
| 04. | IZOD Impact Strength, Parallel to laminate | KJ/m² | >45 |
| 04. | Charpy Impact Strength, Parallel to laminate | KJ/m² | >43 |
| 06. | Electric Strength at 90°C in oil, Perpendicular to laminate | Kv/mm | 9 |
| 07. | Breakdown Voltage at 90°C in oil, Parallel to laminate | Kv | 35 |
| 08. | Proof Tracking Index (CTI) | | >500 |
| 09. | Flammability | | VO |
| 10. | Insulation Resistance | M.Ohm | >5 x 10 ² |
| 11. | Water Absorption Ability | % | 0.06 |

