

# 检测报告 Test Report

报告编号 A2180006948101001E  
Report No. A2180006948101001E

第 1 页 共 4 页  
Page 1 of 4

申请单位 南通和盛电子有限公司

Applicant NANTONG GLORY ELECTRONICS CO.,LTD

地址 江苏省南通市崇川区通富北路 999 号

Address NO.999 TONGFU NORTH ROAD,CHONGCHUAN DISTRICT ,NANTONG, JIANGSU,CHINA

以下测试之样品及样品信息由申请者提供并确认

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

样品名称	龙虾环
Sample Name	Lobster Bands
材质	硅胶
Material	Silicone
供应商	Nantong Glory Electronics Co.,Ltd
Supplier	Nantong Glory Electronics Co.,Ltd
样品接收日期	2018.01.17
Sample Received Date	Jan. 17, 2018
样品检测日期	2018.01.17-2018.01.23
Testing Period	Jan. 17, 2018 to Jan. 23, 2018

## 测试内容 Test Conducted:

根据客户的申请要求，具体要求详见下一页。

As requested by the applicant, for details refer to next page(s).

主 检  
Tested by

南 豪

审 核  
Reviewed by

周 园

批 准  
Approved by

郑晴涛

日 期  
Date

2018.01.23

郑晴涛  
技术经理 Technical Manager

No. 313938473

华测检测认证集团股份有限公司

深圳市宝安区新安街道留仙三路 4 号华测检测大楼

Centre Testing International Group Co.,Ltd.

CTI Building, No.4, Liuxian 3rd road, Xin'an Street, Bao'an District, Shenzhen, P.R.China

# 检测报告 Test Report

报告编号 A2180006948101001E  
Report No. A2180006948101001E

第 2 页 共 4 页  
Page 2 of 4

## 检测结论 Test Conclusion

所检项目的检测结果满足FDA 21CFR 177.2600 拟重复使用的橡胶制品的限值要求。

The results of the test items shown on the report comply with the required limits of FDA 21CFR 177.2600 Rubber articles intended for repeated use.

## 测试摘要 Executive Summary:

### 测试要求

#### TEST REQUEST

FDA 21CFR 177.2600 拟重复使用的橡胶制品 Rubber articles intended for repeated use

- 回流温度下蒸馏水的总浸提物量 Total extractive in distilled water at reflux temperature
- 回流温度下正己烷的总浸提物量 Total extractive in n-hexane at reflux temperature

### 测试结果

#### CONCLUSION

符合 PASS

符合 PASS

符合(不符合)表示检测结果满足(不满足)限值要求。

PASS (FAIL) means that the results shown on the report (do not) comply with the required limits.

\*\*\*\*\*详细结果, 请见下页\*\*\*\*\*

\*\*\*\*\* For Further Details, Please Refer to the Following Page(s) \*\*\*\*\*

# 检测报告 Test Report

报告编号 A2180006948101001E  
Report No. A2180006948101001E

第 3 页 共 4 页  
Page 3 of 4

**FDA 21CFR 177.2600 拟重复使用的橡胶制品 Rubber articles intended for repeated use**

**▼ 回流温度下蒸馏水的总浸提物量 Total extractive in distilled water at reflux temperature**

测试方法 Test Method: FDA 21CFR 177.2600

测试项目 Test Item(s)	结果 Result	方法检出限 MDL	限值 Limit	单位 Unit
	001			
最初 7 小时的总浸提物量 First 7 hours extraction	1.0	0.5	20	mg/in <sup>2</sup>
随后 2 小时的总浸提物量 Succeeding 2 hours extraction	N.D.	0.5	1	mg/in <sup>2</sup>

**▼ 回流温度下正己烷的总浸提物量 Total extractive in n-hexane at reflux temperature**

测试方法 Test Method: FDA 21CFR 177.2600

测试项目 Test Item(s)	结果 Result	方法检出限 MDL	限值 Limit	单位 Unit
	001			
最初 7 小时的总浸提物量 First 7 hours extraction	9.3	0.5	175	mg/in <sup>2</sup>
随后 2 小时的总浸提物量 Succeeding 2 hours extraction	N.D.	0.5	4	mg/in <sup>2</sup>

备注 Remark:

- MDL = 方法检出限 Method Detection Limit
- N.D. = 未检出 (小于方法检出限) Not Detected (<MDL)

**测试样品/部位描述 Tested Sample/Part Description**

001 带有白色印字的蓝色硅胶 Blue silicone with white printing

# 检测报告 Test Report

报告编号 A2180006948101001E  
Report No. A2180006948101001E

第 4 页 共 4 页  
Page 4 of 4

## 样品图片

### Photo(s) of the sample(s)



\*\*\* 报告结束 \*\*\*  
\*\*\* End of Report \*\*\*

#### 声明 Statement:

1. 检测报告无批准人签字、“专用章”及报告骑缝章无效;  
This report is considered invalidated without approval signature, special seal and the seal on the perforation;
2. 样品及样品信息由申请者提供, 申请者应对其真实性负责, CTI 未核实其真实性;  
The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;
3. 本报告检测结果仅对送测样品负责;  
The result(s) shown in this report refer(s) only to the sample(s) tested;
4. 未经 CTI 书面同意, 不得部分复制本报告;  
Without written approval of CTI, this report can't be reproduced except in full;
5. 如检测报告中的英文内容与中文内容有差异, 以中文为准。  
In case of any discrepancy between the English version and Chinese version of the testing reports (if generated), the Chinese version shall prevail.