

FROTH PAK Refill Calibratation Worksheet

Date: _____ Technician: _____

Tank Number: A Side: _____ B Side: _____

Ambient Temperature: _____ Tank Temperature: _____

Perform calibration per instructions.
 Prepare two bags of material, one each A side and B side at the initial set pressures.
 Record data here. Adjust pressures as needed. Stay under 200 psi.
 Continue until ratio is in target range.

Target: 1.05 - 1.15

	A side Pressure	B Side Pressure	A side Weight	B Side Weight	A weight/B weight
Initial	150	130			
Trial 1					
Trial 2					
Trial 3					
Trial 4					
Trial 5					
Trial 6					

Adjustment Guidelines:

If the ratio is: Too High (greater than 1.15) Then: Increase the B Side pressure 5 - 10 psi.

If the ratio is: Too Low (less than 1.05) Then: Increase the A Side pressure 5 - 10 psi.

Note: Maintain pressures below 200 psi. If you are near or over 200 psi, bleed down the system and start over at the initial pressures.