

Silcor® 580

Two-part, low-odour, heavy-duty-trafficable, polyurethane waterproofing membrane

Product Description

A tough, resilient, polyurethane elastomer-based layer rubber barrier giving long-life waterproof protection. It is a premium grade, low VOC elastomer using the latest technology to provide long-life, protective barriers to prestige construction projects.

Features

- Fast application by “flood coating” using a squeegee, without multi-layering
- Long-life, permanently flexible
- Total adhesion — no water tracking
- Fully monolithic structure
- Resistant to puncture and damage
- Resistant to ponded water
- UV-resistant and non-yellowing system
- Hard-wearing, non-slip surface

Combine with other membrane from GCP Applied Technologies to specify a full waterproof envelope

Uses

Silcor® 580 and Silcor Top Coat 80 system are suitable for:

- Exposed roofing, decks and podiums
- Car parks and ramps
- Compactor room floors, plant rooms and wash rooms
- Sport stadium service-ways, plats and vomitories

Silcor 580 Membrane may be used alone as a protective, impact-resistant, resilient, internal flooring to laboratories, sports centres and gymnasium.

The Silcor 580 system can be applied to most clean, dry, stable surface including concrete, precast, fibre cement sheet, CFC, precast, concrete masonry, brick, render, metals and plastics.

Preparation

Surfaces must be sound, smooth and free from dust, laitance, loose matter, oil or other contaminants.

Concrete should be cured 28 days and render 7 days.

Use Silcor LM PU sealant to fill joints, cracks, gaps and form angle fillets to internal corners or penetrations.

Note

Resurfacing of previously painted surfaces will require total removal of existing coatings to expose bare, clean substrate. Machine grinding is the preferred method.



Mix all individual Silcor 580 components with a clean dry stirrer before use.

Preferred application temperature range is between 5 °C and 30 °C.

Application

Priming

To inhibit pin-holes and seal dusty, porous surfaces use one coat of Silcor Primer BS at 8 to 10m² /kg and allow to dry.

Use Silcor Primer BW F100 to seal any damp or green concrete. Roughen PVC or stainless steel before priming with Silcor Primer BW F100.

Mixing

Measure each individual Silcor 580 Membrane Polyol and Isocyanate component accurately by weight into a clean container and mix thoroughly with an electric stirrer (300rpm). Preferred material mixing and application condition is 10 °C - 30 °C and RH <85%.

Application

Silcor 580 Membrane

Apply in one coat by 3mm notched trowel/notched squeegee to give a minimum Wet Film Thickness (WFT) of 1.6mm and minimum required DFT of 1.5mm (approximately 2kg / m²). High-output, single-component, airless spray can be used (contact GCP Applied Technologies for technical advice). Apply Silcor Top Coat 80 non-slip top coat for a standard, non-slip finish as detailed below.

Where a high rating non-slip finish is required, apply membrane by

Typical Properties

| Property | Typical Value | Test Method |
|---|---------------|-------------|
| Colour | Grey | - |
| Specific Gravity | 1.2g / mL | - |
| Solids % Vol | > 97 | - |
| Cure Time - Ready for Flood Test, Tiling, Topping | 48 hours | - |
| Mix Ratio (w/w) | 1 : 1 | - |
| Pot Life (20°C) | 30 minutes | - |
| Tensile Strength | > 8.8MPa | ASTM D412 |
| Elongation | > 350% | ASTM D412 |
| Shore A Hardness | 80 ± 5 | ASTM D2240 |
| Chemical Resistance | Excellent | ASTM C543 |

a two stage process as follows:

Apply first coat by 3mm notched trowel/notched squeegee, as described above. Allow to cure for minimum 12 hours to maximum 24 hours, then apply a second coat at 0.3mm WFT (approximately 0.4kg / m²). While still wet, broadcast with non-slip aggregate. Allow to cure a minimum 12 hours, remove loose aggregate and apply Silcor Top Coat 80 as detailed below.

Silcor Top Coat 80

Apply Silcor Top Coat 80 by roller or air-less spray system at 0.2 to 0.3kg / m². Allow 24 hours curing before foot traffic. Total dry film thickness of system to be 1.5 to 2.0mm.

Surfacing

The finished Silcor 580 Membrane may be subjected to foot traffic 8 hours after installation but 5 days curing should be allowed before vehicles are driven over the surface.

If required for functional or aesthetic reasons, areas of Silcor 580 membrane may be covered with optional surfacing systems, after full curing.

- **Tiles**

Lay ceramic tiles on mortar bed or apply sand layer before application of suitable adhesive.

- **Landscaping**

Use Bituthene® Protection Board or Hydroduct® Drainage Board followed by landscaping.

- **Rigid Surfaces**

Use 0.2mm polyethylene slip-sheet under concrete toppings. Lay paving slabs supported on mortar bed.

Packaging

Silcor 580 36kg set

Shelf Life

Do not store product exposed to weather and sun. When kept in a cool, dry, protected area, sealed pails have a 12-month shelf life at 25°C, 60% RH, but once opened, may solidify within a few days.

Clean Up

Use methylated spirits before curing. Exercise care when using solvent, review all Material Safety Data Sheet (MSDS) before use.

Health and Safety

In case of spills and accidents, refer to the MSDS of the products or when in doubt contact your local GCP representative.

Always wear protective clothing, gloves and protective goggles when handling chemical products. For full information, consult the relevant MSDS.

Project Specification

GCP Applied Technologies offers a comprehensive package of quality and proven systems to meet different project and application needs. Contact your local GCP representative for further information.

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898
India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133
Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168


We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Silcor, Bituthene and Hydroduct are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 04/16 | 300-Silcor-100



gcp applied technologies