



550 Industrial Drive Galt,
CA 95632
(209) 745-2387; (209)
745-5894 fax
Website:

Carson's Coatings Acrylic Finishes

DESCRIPTION:

Carson's Finishes are manufactured with a high-grade, pure acrylic emulsion binder, high quality aggregates and proprietary additives that produce a superior, finish product. Carson's Finishes provide a versatile material, which when properly applied will enhance the appearance of any plastered structure. Carson's Finishes may be sprayed or floated to achieve a smooth, a sand, a dash textured appearance or a light coarse plus worm drive.

BASIC USES:

Carson's Finishes are designed for use as a finish coat, specifically as a higher-grade finish for the home and building industry. Carson's Finishes help bridge the hairline structural and shrinkage cracks inherent in traditional Portland cement plaster construction. Furthermore, they may be used as a high grade finish for any One-Coat Systems, standard three-coat system, properly prepared CMU block, poured in place/tilt up concrete, or as an interior finish over various types of wall boards and other interior wall and ceiling surfaces

COLOR:

Carson's Finishes are packaged white and may be colored using the Carson's Color Bottle System.

PACKAGING:

Carson's Finishes are packaged in 64lb. (29.03kg) 5 gallon (18.9L) Pails.

STORAGE:

1. Store pails in a cool, dry location.
2. Store at a temperature between 40°F (4°C) and 90°F (32°C).
3. Do not store in direct contact with the ground and/or concrete.
4. Store out of direct sunlight.
5. Protect pails from weather and other damage.

COVERAGE:

Coverage will vary depending on surface preparation, ambient temperature, surface temperature, aggregate size and/or application methods. The coverage for Carson's Finishes range from approximately 100ft² (9m²) to 140ft² (13m²).

AREA OF USE:

Carson's Finishes may be applied to the following substrates. For best results, surfaces should be treated with Carson's Base Primer.

1. One-Coat Products
2. Brown Coat
3. Stucco
4. Poured in place and/or tilt- up concrete
5. All Carson's Base Coats
6. Masonry and CMU Block
7. Properly prepared Dry Wall
8. Other substrates as approved by Carson's Coatings.

NOTE: Carson's Finishes are not intended for application over EIF Systems.

SURFACE PREPARATION:

All surfaces to receive application must be clean and free of loose debris, dirt and dust, efflorescence, grease, oils, curing agents, and cleaning solutions. Ensure that all surfaces are smooth and free of any irregularities. Repair all cracks with the appropriate patching material for the existing substrate. Painted or glossy surfaces must be roughened to ensure a proper bond. It is recommended that all approved substrates be coated with Carson's Base Primer to enhance the material's performance. One coat and three coat stucco products must be cured for a minimum of 7 days and concrete must cure for a minimum of 28 day prior to the application of this material. The pH level of these products must be below 10 prior to application of the Base Primer or Carson's Finishes.

MIXING:

1. Refer to the Carson's Color Bottle System Product Data Sheet for color mixing instructions.
2. Carson's Finishes must be thoroughly mixed prior to use with a Jiffy-type mixer.
3. If multiple pails are being used intermix pails to achieve consistency.

APPLICATION:

Carson's Finishes may be applied using a hand application method or a machine sprayed method.

Hand Application Method

1. Ensure that the receiving surface has been properly prepared according to the Surface Preparation section of the Product Data Sheet.
2. Apply a uniform coat of the desired Carson's Finish, no thicker than the largest aggregate, to the substrate.

3. Immediately following the applicator, use a plastic float or stainless steel trowel in a consistent motion to obtain the desired finish.

Machine Sprayed Method

1. Add desired amount of mixed material to sprayer.
2. Begin spraying material onto the receiving surface. Starting at a corner and not stopping until the opposing corner is reached. Avoid puddling.
3. To ensure consistent color a uniform thickness must be maintained during the application process.
4. A true dash finish usually required 2 to 3 coats.

DRYING:

Drying time may vary due to climatic conditions, but should not take less than 24 hours at an ambient and surface temperature of 70°F (21°) and 55% R.H. Variations in ambient and surface temperature and humidity may prolong drying time. All freshly applied material must be protected by an approved protective system from inclement weather until fully dry and cured. It is the responsibility of the applicator to determine if the product is fully dry prior to exposing it to rain, snow, dew, and/or any other inclement weather condition that may be detrimental to the product.

LIMITATIONS:

DO NOT use as a finish in any EIF system Application.

DO NOT apply product when the ambient and surface temperature is below 40°F/4°C or above 90°F/32°C. The ambient and surface temperature must stay consistently within this range until fully cured (see also CURING and Drying). Material that is allowed to freeze may

suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully cured. It is the sole responsibility of the applicator to determine when this product is fully cured and/or dry.

DO NOT apply Carson's Finishes if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and oils.

DO NOT add any more water than is prescribed when diluting the product.

DO NOT deviate in the mixing or application procedures contained in this or related Product Information Sheet(s).

DO NOT use a Jiffy-Type mixer that exceeds 500RPM

CLEANING:

Clean up may be accomplished with water immediately after use.

NOTE:

Failure to follow manufacturers written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off; and overall system failure.

Due to job conditions beyond the control of Carson's Coatings we make no warranty as to the acceptance of the final color. The actual integrally colored finish should be applied on a sample section of the project and verified for color accuracy prior to the actual application process.

SAFETY:

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

DISCLAIMER:

Carson's Coatings [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use of the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

CLAIMS:

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Carson's Coatings reasonable charges, including travel and labor associated with investigation of such claim.

TECHNICAL ASSISTANCE:

Technical assistance and information is available by calling Carson's Coatings at (209) 745-2387 or FAX (209) 745-5894 or by e-mail at "info@carsoncoatings.com".

WARRANTY:

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.