

# KetaSpire® KT-820

Polyetheretherketone

Solvay Specialty Polymers

PROSPECTOR®

www.ulprospector.com

## Technical Data

### Product Description

KetaSpire® KT-820 is a low flow grade of unreinforced polyetheretherketone (PEEK) supplied in a lubricated pellet form. KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity, and excellent chemical resistance to organics, acids, and bases.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing, and other industrial uses. KetaSpire® KT-820 can be easily processed using typical injection molding and extrusion processes. This resin is also available as KetaSpire® KT-820P in a natural-color coarse powder form for compounding.

Pellets of KT-820 are supplied lightly dusted with the lubricant calcium stearate (0.01% level) to aid with pellet conveyance in plastication screws. The equivalent non-lubricated natural color grade of low flow KetaSpire® is available as KT-820 NL.

- Black: KT-820 BK 95
- Natural: KT-820 NT

### General

Material Status	• Commercial: Active
Literature <sup>1</sup>	• <a href="#">Technical Datasheet</a>
UL Yellow Card <sup>2</sup>	• <a href="#">E140728-100211981</a>
Search for UL Yellow Card	• <a href="#">Solvay Specialty Polymers</a> • <a href="#">KetaSpire®</a>
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Additive	• Lubricant
Features	• Autoclave Sterilizable • Ductile • E-beam Sterilizable • Ethylene Oxide Sterilizable • Fatigue Resistant • Flame Retardant • Good Chemical Resistance • Good Dimensional Stability • Good Impact Resistance • Good Sterilizability • Heat Sterilizable • High Heat Resistance • Radiation (Gamma) Resistant • Radiation Sterilizable • Radiotranslucent • Steam Resistant • Steam Sterilizable
Uses	• Aircraft Applications • Automotive Applications • Connectors • Dental Applications • Electrical/Electronic Applications • Film • Gears • Hospital Goods • Housings • Industrial Applications • Medical Devices • Medical/Healthcare Applications • Oil/Gas Applications • Pump Parts • Seals • Surgical Instruments • Tubing
Agency Ratings	• FAA FAR 25.853a <sup>3</sup> • ISO 10993
RoHS Compliance	• RoHS Compliant
Appearance	• Black • Natural Color
Forms	• Pellets <sup>4</sup>
Processing Method	• Extrusion Blow Molding • Film Extrusion • Injection Molding • Machining • Profile Extrusion • Thermoforming • Wire & Cable Extrusion
Multi-Point Data	• Isothermal Stress vs. Strain (ISO 11403-1) • Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value Unit	Test Method
Specific Gravity	1.30 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	3.0 g/10 min	ASTM D1238
Molding Shrinkage <sup>6</sup>		ASTM D955
Flow	1.1 to 1.3 %	
Across Flow	1.3 to 1.5 %	
Water Absorption (24 hr)	0.10 %	ASTM D570



Mechanical	Nominal Value Unit	Test Method
Tensile Modulus		
-- <sup>7</sup>	3500 MPa	ASTM D638
--	3830 MPa	ISO 527-2/1A/1
Tensile Stress		
Yield	96.0 MPa	ISO 527-2/1A/50
-- <sup>7</sup>	95.0 MPa	ASTM D638
Tensile Elongation		
Yield <sup>7</sup>	5.2 %	ASTM D638
Yield	4.9 %	ISO 527-2/1A/50
Break <sup>8</sup>	78 %	ASTM D638
Break <sup>7</sup>	20 to 30 %	ASTM D638
Break	20 to 30 %	ISO 527-2/1A/50
Flexural Modulus	3700 MPa	ASTM D790 ISO 178
Flexural Strength		
--	146 MPa	ASTM D790
--	121 MPa	ISO 178
Compressive Strength	118 MPa	ASTM D695
Shear Strength	84.1 MPa	ASTM D732
Poisson's Ratio	0.33	ASTM E132
Impact	Nominal Value Unit	Test Method
Notched Izod Impact		
--	91 J/m	ASTM D256
--	9.2 kJ/m <sup>2</sup>	ISO 180
Unnotched Izod Impact	No Break	ASTM D4812 ISO 180
Hardness	Nominal Value Unit	Test Method
Rockwell Hardness (M-Scale)	97	ASTM D785
Durometer Hardness (Shore D, 1 sec)	88	ASTM D2240
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load <sup>9</sup>		ASTM D648
1.8 MPa, Annealed, 3.20 mm	157 °C	
Glass Transition Temperature	150 °C	ASTM D3418
Peak Melting Temperature	340 °C	ASTM D3418
CLTE - Flow (-50 to 50°C)	4.3E-5 cm/cm/°C	ASTM E831
Specific Heat		DSC
50°C	1560 J/kg/°C	
200°C	2150 J/kg/°C	
Thermal Conductivity	0.24 W/m/K	ASTM E1530
Electrical	Nominal Value Unit	Test Method
Surface Resistivity	> 1.9E+17 ohms	ASTM D257
Volume Resistivity	1.6E+17 ohms·cm	ASTM D257
Dielectric Strength		ASTM D149
0.0508 mm, Amorphous Film	200 kV/mm	
1.60 mm	20 kV/mm	
3.00 mm	15 kV/mm	
Dielectric Constant		ASTM D150
60 Hz	3.06	
1 kHz	3.10	
1 MHz	3.05	



Electrical	Nominal Value Unit	Test Method
Dissipation Factor		ASTM D150
60 Hz	1.0E-3	
1 kHz	1.0E-3	
1 MHz	3.0E-3	
Flammability	Nominal Value Unit	Test Method
Flame Rating		UL 94
0.800 mm	V-1	
1.60 mm	V-0	
Oxygen Index	37 %	ASTM D2863
Fill Analysis	Nominal Value Unit	Test Method
Melt Viscosity (400°C, 1000 sec <sup>-1</sup> )	440 Pa·s	ASTM D3835

**Additional Information**

Standard Packaging and Labeling

- KetaSpire resins are packaged in polyethylene buckets or cardboard boxes depending upon the order size. Individual packages will be plainly marked with the product, color, lot number, and net weight.

Injection	Nominal Value Unit
Drying Temperature	150 °C
Drying Time	4.0 hr
Rear Temperature	355 °C
Middle Temperature	365 °C
Front Temperature	370 °C
Nozzle Temperature	375 °C
Mold Temperature	175 to 205 °C
Injection Rate	Fast
Screw Compression Ratio	2.5:1.0 to 3.5:1.0

**Injection Notes**

Drying

- KetaSpire resins must be dried completely prior to melt processing. Incomplete drying will result in defects in the formed part ranging from surface streaks to severe bubbling. Pellets can be dried on trays in a circulating air oven or in desiccating hopper dryer. Drying conditions recommended are 4 hours at 150°C (300°F).

Injection Molding

- KetaSpire resins can be readily injection molded in most screw injection machines. A general purpose screw with a compression ratio in the range of 2.5 - 3.5 : 1 is recommended, as is minimum back pressure. Injection speeds should be as fast as possible, consistent with part appearance requirements. Mold temperatures in the range of 175°C to 205°C (350°F to 400°F) are suggested. Recommended starting point barrel temperatures are shown in the following table.

**Notes**

<sup>1</sup> These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

<sup>2</sup> A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

<sup>3</sup> Passes 60s VB flame, smoke & toxicity requirements.

<sup>4</sup> Pellets are supplied lightly dusted with the lubricant calcium stearate (0.01% level). For non-lubricated, natural color grade order KT-820 NL.

<sup>5</sup> Typical properties: these are not to be construed as specifications.

<sup>6</sup> 0.125"x0.5"x5" bar

<sup>7</sup> 50 mm/min

<sup>8</sup> 5.0 mm/min

<sup>9</sup> 2 hours at 200°C



---

## Where to Buy

---

### Supplier

#### **Solvay Specialty Polymers**

Alpharetta, GA USA

**Telephone:** 800-621-4557

**Web:** <http://www.solvayspecialtypolymers.com/>

---

### Distributor

#### **ALBIS Plastic**

*ALBIS Plastic is a global distribution and compounding company. Contact ALBIS Plastic for availability of individual products per country.*

**Telephone:** +49-40-78105-0

**Web:** <http://www.albis.com/>

**Availability:** Belgium, Bulgaria, Czech Republic, Denmark, Estonia, Finland, France, Germany, Hungary, Ireland, Latvia, Lithuania, Luxembourg, Netherlands, Norway, Poland, Portugal, Romania, Russian Federation, Slovakia, Slovenia, Spain, Sweden, Turkey, United Kingdom

