

ALL SERVICE JACKET w/SSL TAPE

VentureTape[®] 1541S is a non-adhesive kraft/scrim/foil laminate (ASJ) with a 1 7/32" strip of acrylic adhesive lengthwise (35.5") along one edge of the sheet for use as a self seal lap (SSL). Designed for use as a vapor barrier jacket on all types of pipe insulation, Venture Tape 1541S applies easily and excels in demanding temperature and humidity applications.

Meets ASTM C1136, Type I, II, III, IV			
FACING COMPOSITION Foil	DESCRIPTION Aluminum	VALUES (ENGLISH) 0.0003 inch	VALUES (METRIC) 7.6 micron
Barrier Coating	Elastomeric Polymer	0.0002 inch	5.1 micron
Reinforcing	Tri-directional Fiberglass	5 / inch (MD) 5 / inch (XD)	20 / 100 mm (MD) 20 / 100 mm (XD)
Adhesive	Flame Resistant		
Kraft	High Intensity White	45 lbs / 3000 ft ²	73 g / m²
PHYSICAL PROPERTIES Basis Weight	TEST METHOD Scale	VALUES (ENGLISH) 29 lbs / 1000 ft ²	VALUES (METRIC) 142 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hr [.] ft ^{z.} in Hg)	1.15 ng / N [·] s
Bursting Strength	ASTM D774	65 psi	4.6 kg / cm²
Puncture Resistance	ASTM C1136	85 beach units	2.5 Joules
Tensile Strength	ASTM C1136	55 lbs/inch width (MD) 50 lbs/inch width (XD)	9.6 kN / m (MD) 8.8 kN / m (XD)
Caliper / Thickness	Micrometer	0.009 inch	229 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Emissivity	ASTM E408	0.03	0.03

Contact Venture Tape today for a complete list of products or a free sample

Toll Free North America 800-343-1076 From United Kingdom 0-800-962-957 From Australia 1-800-122-797 www.venturetape.com



GTA - NHT, Inc. Venture Tape 30 Commerce Rd., Rockland, MA 02370 Tel 781-331-5900; Fax 781-871-0065 800-343-1076 (U.S.A.), 800-544-1024 (Canada) Toll Free Fax 877-264-5490 www.venturetape.com

