



OLD WESTERN PAINT CO., INC.

2001 West Barberry Place
Denver, Colorado 80204

PHONE: 303-825-5147

FAX: 303-825-2437

TOLL FREE: 1-888-POLY VAR
(765-9827)

www.oldwesternpaint.com
www.polyvar.com

PRODUCT INFORMATION

POLY FAUX

Polyurethane Faux Coating

Imperial Gold, Silhouette Black, Abyss Blue, Silky Chocolate, Royal Brown, Robust Red, Carmel Coffee

TYPE: One packaged oil modified
100% pure polyurethane.

DESCRIPTION: POLY FAUX

Polyurethane is a unique, durable interior coating system designed to help create a rich faux stain look. For use on wood and concrete floors. **POLY FAUX** can brighten up any old worn wood or concrete floor. Perfect for stained or discolored wood or concrete floors. Brings new life to any room with many color choices to meet your specific needs. Easy to maintain. To change color, simply recoat, giving a new faux or stain look.

CLEAN UP: Mineral Spirits or Paint Thinner

APPLICATION:

Brush, Flat Pad Applicator, Wool Pad.
Surface should be free from dust, dirt, wax, peeling paint or any loose substance. Surface must be screened and completely dry.
First coat: Apply a generous coat by swirling applicator to achieve a faux look, or pull straight for an even look, maintaining a wet edge throughout the coating job. Let dry completely, approximately 8-12 hours.
Second coat: After 12 hours or when dry, and before 48 hour hard dry, apply using first coat method.
If dry time of first coat exceeds 48 hours, screen, for good adhesion, tack, then apply second coat. The use of a different color on the second coat will help achieve a contrasting faux design.
Two coats recommended. Can top coat with *Poly Var* Clear Polyurethane in desired sheen.
Do not apply over steared sanded sealers. Not recommended for garage floors, not suited for hot tire pick-up.

SPREADING RATE:

First coat: 350 – 400 square feet per gallon.
Second coat: 400 – 450 square feet per gallon.
Spreading rate subject to surface porosity, texture and application method.

DRYING TIME:

Dries in 2-4 hours (dust-free), recoat 12 hours or when completely dry. Drying time may be affected by excessive humidity, low temperature, failure of air movement and thickness of finish.

ANALYSIS:

SOLIDS BY WEIGHT	49.00%
SOLIDS BY VOLUME	41.00%
SOLVENT TYPE	Aliphatic

GLOSS 60 Degree:

Gloss	95-97
Semi Gloss	64-70
Velvet	34-40
Satin	28-34

MAINTENANCE:

Allow coating to cure completely. Always clean well with *Poly Glow Hardwood Floor Maintainer*. *Poly Glow* leaves no residue and assures a clean, beautiful sheen that alleviates complications if future coating is desired. *Poly Glow* is 100% biodegradable and pH-neutral, safe to use on almost any hard surface.

Available in: 1200PFS Satin, 1200PFV Velvet, 1200PFSG Semi Gloss and 1200PFG Gloss