

PRODUCT DATA SHEET

SikaCim® Paver

COMPACTION AID FOR NO-SLUMP CONCRETE PRODUCTS

DESCRIPTION

SikaCim® Paver is a compaction aid for no-slump concrete.

This admixture technology has been specifically developed for use in low cement content no-slump mixes.

USES

SikaCim® Paver is used for producing optimised no-slump concrete with a low moisture content. No-slump concrete production is generally used in the manufacture of machine-made concrete products associated with instant demoulding such as:

- Kerbstones
- Pipes
- Edgings and other items for garden and landscape design

CHARACTERISTICS / ADVANTAGES

SikaCim® Paver offers substantial benefits to the producer of no-slump concrete products:

- Efficient dispersion and distribution of cement, additives and pigments

- Improved movement of the concrete through the machine (faster mould filling)
 - Optimised compaction with shorter pressing time and increased throughput (shorter production cycle)
 - Increased “green” strength on immediate de-moulding (keeps the shape of freshly de-moulded semi-dry concrete products because it prevents slumping after de-moulding)
 - More economic concrete mix designs
 - Create superior products
- SikaCim® Paver allows for the following advantages in the finished concrete products:
- Closer textured and more uniform surfaces
 - Consistent product quality due to a homogenous concrete mix
 - Increased density
 - Less variation in densities and strengths across the area of the mould (constant spread of density & strength over the pallet)
 - Minimized damage due to early handling
 - Enhanced ultimate compressive and tensile strengths
 - Less customer returns and second grade product

PRODUCT INFORMATION

Chemical base	Ligno sulfonate blend
Packaging	900 mL Jerrycan
Appearance / Colour	Liquid / brown
Shelf life	12 months from date of production if stored properly in original, unopened packaging.
Storage conditions	Protect from frost, direct sunlight and contamination. When it is delivered in bulk, the tanks and equipment used must be free of residues from previous deliveries.
Density	1.15 ± 0.01 kg/L (at +25 °C)

APPLICATION INFORMATION

Recommended Dosage

900 mL for \pm 3 - 4 bag cement (50 kg)

APPLICATION INSTRUCTIONS

DISPENSING

In general a mixing time of at least 30 seconds is essential, although the actual mixing time after adding the admixture depends on the individual circumstances and should be determined by trials.

LIMITATIONS

SikaCim® Paver can be added with the mixing water or introduced at the end of the mixing process.

SikaCim® Paver must not be used for wet cast concrete as this could result in excessive air entrainment and subsequent loss of strength.

Before use suitability tests must be performed.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia

Jl. Raya Cibinong-Bekasi km.20.

Cileungsi, Bogor 16820 - Indonesia

Tel. +62 21 8230025

Fax. +62 21 8230026

Website: idn.sika.com

email: sikacare@id.sika.com



SikaCimPaver_en_ID_(08-2017)_1_1.pdf

Product Data Sheet

SikaCim® Paver

August 2017, Version 01.01

021303011000000363