

Sikadur® Aggregates

Content:

1	Sikaflour (SF45).....	2
2	Sikadur® 500	2
3	Sikadur® 501	2
4	Sikadur® 502	2
5	Sikadur® 504	2
6	Sikadur® 505	2
7	Sikadur® 506	2
8	Sikadur® 507	2
9	Sikadur® 508	3
10	Sikadur® 509	3
11	Sikadur® 510	3
12	Sikadur® 512	3
13	Sikadur® 584	3



Sikafloor® (SF45)

For use as	Filler/Extender
Aggregate size	< 0.045 mm
Dry bulk density	~ 1.4 kg/litre
Packaging	25 kg bags

Sikadur® 500

For use as	Aggregate
As component C for	Sikadur®-43 repair mortar
Aggregate size	0.08 – 1.70 mm
Dry bulk density	~ 1.7 kg/litre
Packaging	25 kg bags

Sikadur® 501

For use as	Non-skid surfacing for Sikafloor® self-levelling flooring compound
As component C for	Sikadur®-41 patching mortar
Aggregate size	0.3 – 0.9 mm
Dry bulk density	~ 1.5 kg/litre
Packaging	25 kg bags

Sikadur® 502

For use as	Aggregate
As component C for	Sikadur®-42 castable grout
Aggregate size	maximum 1.7 mm
Dry bulk density	~ 1.7 kg/litre
Packaging	25 kg bags

Sikadur® 504

For use as	Aggregate
As component C for	Sikafloor®-261 self-levelling flooring compound
Aggregate size	0.08 – 0.20 mm
Dry bulk density	~ 1.5 kg/litre
Packaging	25 kg bags

Sikadur® 505

For use as	Non-skid surfacing for Sikafloor® self-levelling flooring compound
Aggregate size	0.1 – 0.5 mm
Dry bulk density	~ 1.4 kg/litre
Packaging	25 kg bags

Sikadur® 506

For use as	Aggregate
As component C for	Sikafloor® flooring screed
Aggregate size	special mix
Dry bulk density	~ 1.8 kg/litre
Packaging	25 kg bags

Sikadur® 507

For use as	Surface finish for Sikafloor® flooring screed
Aggregate size	special mix
Dry bulk density	~ 1.8 kg/litre
Packaging	25 kg bags

Sikadur® 508

For use as	Non-skid surfacing for Sikafloor® self-levelling flooring compound
As component C for	Sikafloor® -381
Aggregate size	0.1 – 0.3 mm
Dry bulk density	~ 1.7 kg/litre
Packaging	25 kg bags

Sikadur® 509

For use as	Non-skid surfacing
As component C for	Sikafloor® -Parkdeck
Aggregate size	0.7 – 1.2 mm
Dry bulk density	~ 1.5 kg/litre
Packaging	25 kg bags

Sikadur® 510

For use as	Non-skid surfacing
As component C for	Sikafloor® -81 EpoCem mortar mix
Aggregate size	2.0 – 3.2 mm
Dry bulk density	~ 1.5 kg/litre
Packaging	25 kg bags

Sikadur® 512

For use as	Aggregate
As component C for	SikaPronto® -11SL / Sikagrout® -214
Aggregate size	2 – 8 mm
Dry bulk density	~ 1.7 kg/litre
Packaging	25 kg bags

Sikadur® 584

For use as	Aggregate
Aggregate size	0.07 – 2.00 mm
Dry bulk density	~ 1.5 kg/litre
Packaging	25 kg bags



Sika Singapore Pte Ltd
200 Pandan Loop, 06-02 Pantech 21
Singapore 128388
SINGAPORE

Phone: +65 6777 2811
Fax: +65 6779 6200
e-mail: info@sg.sika.com
www.sika.com.sg

Sika Kimia Sdn Bhd
Lot 689 Nilai Industrial Estate
71800 Nilai, Negeri Sembilan DK
MALAYSIA

Phone: +6 06 799 1762
Fax: +6 06 799 1980
e-mail: info@my.sika.com
www.sika.com.my

