


Color Chart


PREMO Colorfast45® Paint System







SR = 0.50 SRI = 58



Mocha Tan (22) SR = 0.52 TE = 0.87 **SRI = 60**



Antique Bronze (D4) SR = 0.36 TE = 0.88 **SRI = 39**



Taupe (74) SR = 0.44TE = 0.87 SRI = 49



Ash Grey (25) SR = 0.37 TE = 0.88 SRI = 40



Charcoal (17) SR = 0.30 TE = 0.87 SRI = 31



Brown (12) SR = 0.31 TE = 0.87SRI = 32



Dark Brown (44) SR = 0.27 TE = 0.87 SRI = 27



Forest Green (26) SR = 0.27 TE = 0.87 SRI = 27



Fern Green (07) SR = 0.30 TE = 0.88SRI = 31



Sierra Green (20) SR = 0.38 TE = 0.87 SRI = 41




SR = 0.30 TE = 0.88 SRI = 31



SR = 0.30 TE = 0.86SRI = 30



Acrylic Coated Galvalume® (41)¹ SR = 0.67 TE = 0.14



Panels are also available in other gauges, please inquire. Not all colors and gauges are stocked at all branches. Color samples are close representations but are limited by processing and viewing conditions. Actual samples are available by request. For all specific warranty, application, installation and technical information regarding these products, contact your sales representative.

PREMO Colorfast45® Paint Performance					
Salt Spray Resistance			Direct and Reverse Impact		
ASTM B 117	1,000 Hours	Creep from scribe no more than 1/8", no blisters	ASTM D 2794	80 in-lbs	No visible paint removal with cellophane tape
Humidity Resistance			Water Immersion		
ASTM D 2247	1,200 Hours	No blisters, cracking or peeling	ASTM D 870	500 Hours	No loss of adhesion (100°F)
Abrasion Resistance			Cross-Hatch Adhesion		
ASTM D 968	Method A	30 liters/mil falling sand	ASTM D 3359	Таре	No paint removal
Chalk Resistance			Color Change		
ASTM D 4214	2,000 Hours	No chalking greater than #8 rating	ASTM D 2244	2000 hours	Not exceed 5 Hunter units
Bend Adhesion			Flame Spread Rate		
ASTM D 4145	2T	No loss of adhesion	ASTM E 84		Class A coating



